

STANDARD REFERENCE:

EN ISO 683-4: 2018 (Hot-rolled products) | EN 10277: 2018 (Bright products)

RODACCIAI REFERENCES AND COMPARABLE STANDARDS

EUROPE		ITALY	GERMANY		FRANCE	UK	USA
EN 10087: 1998 EN 10277-3: 2008		(UNI 4838-80)	(DIN 1651-88)		(NF A 35-562-86)	(BS 970 pt.3-91)	ASTM A 29
Grade	N°		Werkstoff	N°			
44SMn28	1.0762	CF 44 SMn 28	-	-	45 MF 6.3	226M44	1144

CHEMICAL COMPOSITION (CAST ANALYSIS) (%)

C	Si / max	Mn	P / max	S
0,40÷0,48	0,40	1,30÷1,70	0,060	0,24÷0,33

MECHANICAL PROPERTIES - AS ROLLED CONDITION

Size mm	as Rolled and/or as Rolled + Turned (+SH)		as Rolled and/or as Rolled + Turned + Quenched + Tempered (+SH +QT)		
	Hardness HB max	R _m (MPa)	R _{p0,2} (MPa) min	R _m (MPa)	A ₅ (%) min
≥5 ≤10	(266)*	630÷900*	520	700÷850*	16*
>10 ≤16	(252)*	630÷850*	480	700÷850*	16*
>16 ≤40	241	630÷820	420	700÷850	16
>40 ≤63	231	620÷790	410	700÷850	16
>63 ≤100	228	610÷780	400	700÷850	16

*Values valid only for hot rolled products

For size <5 mm the mechanical properties may be agreed at the time of enquiry and order

MECHANICAL PROPERTIES OF BRIGHT STEEL

Size mm	Cold Drawn (+C)			Quenched + Tempered + Peeled (+QT +SH)*			Quenched + Tempered + Cold Drawn (+QT +C)		
	R _{p0,2} (MPa) min	R _m (MPa)	A ₅ (%) min	R _{p0,2} (MPa) min	R _m (MPa)	A ₅ (%) min	R _{p0,2} (MPa) min	R _m (MPa)	A ₅ (%) min
≥5 ≤10	600	760÷1030	5	-	-	-	595	850÷1000	9
>10 ≤16	530	710÷980	5	-	-	-	595	850÷1000	9
>16 ≤40	460	660÷900	6	420	700÷850	16	490	700÷900	11
>40 ≤63	430	650÷870	7	410	700÷850	16	490	700÷900	12
>63 ≤100	390	630÷840	7	400	700÷850	16	490	700÷900	12

*This values are valid also for Cold Drawn - Quenched + Tempered Condition (+C +QT)

For size <5 mm the mechanical properties may be agreed at the time of enquiry and order

WORKING TEMPERATURES RECOMMENDED

Operation	Hot forgings deformation	Normalizing	Soft annealing	Quenching in oil or water	Tempering
°C	950÷1230	850÷880	650÷700	840÷870	540÷680

rev. 10/2018

Mark Rodacciai

Download APP

FREE-CUTTING STEELS
DIRECT-HARDENING
44SMN28
